

## **Technical specifications**

Marmoleum meets the requirements of EN-ISO 24011 Marmoleum Decibel meets the requirements of EN 686

			Marmoleum Striato original, colour, textura	Marmoleum Striato Decibel	
	Total thickness	EN-ISO 24346	2,5 mm	3,5 mm	
	Surface finish		Topshield <sup>2</sup>	Topshield <sup>2</sup>	
â Mì	Domestic use	EN-ISO 10874	Class 23, heavy	Class 23, heavy	
# <i>111</i> 0	Commercial use	EN-ISO 10874	Class 34, very heavy	Class 33, heavy	
m <i>m</i> ì	Light Industrial use	EN-ISO 10874	Class 43, heavy	Class 41, moderate	
Ē.	Roll width	EN-ISO 24341	2,00 m	1,95 m / 2,00 m	
J	Roll length	EN-ISO 24341	≤ 33 m	≤ 33 m	
F	Residual indentation Typical value	EN-ISO 24343-1	≤ 0,15 mm ~ 0,08 mm	≤ 0,30 mm ~ <i>0,20 mm</i>	
ß	Total weight typical value	EN-ISO 23997	2900 g/m <sup>2</sup>	3100 g/m <sup>2</sup>	
6	Castor chair continous use	EN 425 (ISO 4918)	Suitable for office chairs with castors		
R	Light fastness	EN-ISO 105-B02	Method 3: blue scale minimum 6		
P	Flexibility	EN-ISO 24344	Ø 40 mm	Ø 40 mm	
	Resistance to chemicals	EN-ISO 26987	Resistant to diluted acids, oils, fats and to conventionals solvents. Not resistant to prolonged exposure to alkalis.		
ø	Bacteriostatic properties*		Marmoleum has natural bacteriostatic properties, which are confirmed by independent laboratories, even against the bacteria MRSA.		
	Cigarette resistance	EN 1399	There is no melting of the surface b	y cigarettes. Marks left on Marmoleum t cigarettes can be removed.	
25	Slip resistance	DIN 51130	R9 Textura R10	R9	
9	Acoustical impact sound reduction	EN-ISO 717-2	≤5 dB	Make to order with foam backing: 18	
	Indoor Air Emissions: TVOC at 28 days	EN 16516	< 0,05 mg/m <sup>3</sup>	< 0,05 mg/m <sup>3</sup>	
LCA			LCA is the foundation for securing the lowest environmental impact.		
Ì	Creating better environments				
¢ بر	CO, neutral		Marmoleum Striato original, colour and textura		
	renewable electricity		are produced CO <sub>2</sub> neutral (cradle to gate).** Marmoleum is manufactured using 100% electricity from renewable sources.		
		······		Marmoleum and Marmoleum Decibel are made of 94-98% natural materials.	
			Marmoleum contains PEFC certified wood flour.		
	natural materials (e.g. linseed oil, jute, tree resin, wood flour, limestone)			Marmoleum and Marmoleum Decibel are free of PVC, PET, synthetic rubber and plasticiz	
				REACH compliant.	
23	recycled content		Marmoleum contains recycled content.		
	Application on underfloor heating		yes	yes	
	Marmoleum meets the requirements of EN 140	41			
CE	Product code	EN 14041	0100201_DoP_306	0100207_DoP_306	
G st CS	Reaction to fire	EN 13501-1	C <sub>n</sub> - s1, G, CS	C <sub>n</sub> - s1, G, CS	
°%≦n ≥0,30	Slip resistance	EN 13893	μ ≥ 0,30	$\mu \ge 0,30$	
	Body voltage	EN 1815	< 2 kV	< 2 kV	
<sup>°</sup> λ <sub>23</sub> ttt	Thermal conductivity	EN 12524	0,17 W/m·K		

\* Marmoleum sheet can be installed nett fit, or with a welding rod in the seam. Both are proven hygienic solutions. \*\* For verification and details please consult our Marmoleum EPD.

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001. All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001. The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites.

HI R ISO 9001

