




| | PRODUCT CHARACTERISTICS | | | |
|---|-------------------------|-------------|-------------------|--|
| | Standard | Requirement | Unit | Results |
| PRODUCT DESCRIPTION | | | | |
| Surface treatment | - | - | - | PUR PROTECT |
| Surface complex | - | - | - | 100% PVC |
| Foam | - | - | - | Mousse à cellules fermées |
| Thickness | EN 428 | - | mm | 4.5 mm  |
| Weight | EN 430 | - | kg/m ² | 2,6 |
| Length | EN 426 | - | lm | 20.5 Standard |
| Width | EN 426 | - | lm | 1,5 |
| SPORT PROPERTIES | | | | |
| Shock absorption | EN 14808 | ≥ 25 | % | ≤ 25 |
| Vertical deformation | EN 14809 | ≤ 3.5 | mm | ≤ 3.5 |
| Energy return | NF P 90 203 | ≥ 0.31 | m/s | ≥ 0.31 |
| Sliding coefficient | EN 13036-4 | 80 to 110 | - | 80 - 110 |
| Ball bounce | EN 12235 | ≥ 90 | % | ≥ 90 |
| Ball speed | UEFA | 50 to 65 | cm | - |
| | ITF | - | - | - |
| TECHNICAL CHARACTERISTICS | | | | |
| Abrasion resistance | EN ISO 5470-1 | ≤ 1000 | mg | ≤ 350 |
| Impact resistance | EN 1517 | ≥ 8 | N/m | ≥ 8 |
| Indentation resistance | EN 1516 | ≤ 0.5 | mm | ≤ 0.5 |
| CLASSIFICATION | | | | |
| Feu | EN 13501-1 | - | - |  |
| DECLARATION OF PERFORMANCE | | | | |
|  | DOP n°xxx | - | - | Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load |

| | INSTALLATION METHODS | | |
|---------------------------------------|-----------------------------------|------|---|
| | Gerflor's recommendation | Unit | Results |
| Glued installation: "Original" | Level of dampness of the subfloor | % | RH < 80% (BS 8203) or < 4.5% humidity (CCM) |
| Installation on Isolsport: "Flexible" | | % | RH < 80% (BS 8203) or < 7.0% humidity (CCM) |

| COLOUR RANGE | |
|---|-----------------------|
|  | Standard roll 20.5 lm |