



DESCRIPTION			
Total thickness	EN 428	mm	2.20
Thickness of wearlayer	EN 429	mm	1.14
Weight	EN 430	g/m ²	2900
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	K5
Fire rating	EN 13501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip dry resistance : Pendulum Tester	BS 7976	PTV	≥ 36
Surface roughness R _{tm}	-	µm	R _z ≥ 20
Slip resistance wet: ramp test with oil	DIN 51 130	class	R11
PERFORMANCE			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	EN 649	group	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	
CE MARKING			
	EN 14041	-	
		-	